



AFRL-OSR-VA-TR-2015-0152

---

## **EUO--BASED MULTIFUNCTIONAL HETEROSTRUCTURES**

**Darrell Schlom  
CORNELL UNIVERSITY**

---

**07/06/2015  
Final Report**

**DISTRIBUTION A: Distribution approved for public release.**

**Air Force Research Laboratory  
AF Office Of Scientific Research (AFOSR)/ RTD  
Arlington, Virginia 22203  
Air Force Materiel Command**

<b>REPORT DOCUMENTATION PAGE</b>				<i>Form Approved</i> OMB No. 0704-0188	
<small>The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to the Department of Defense, Executive Service Directorate (0704-0188). Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.</small>					
<b>PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ORGANIZATION.</b>					
<b>1. REPORT DATE (DD-MM-YYYY)</b> 15-06-2015		<b>2. REPORT TYPE</b> Final		<b>3. DATES COVERED (From - To)</b> April 2010 - April 2015; June 2015	
<b>4. TITLE AND SUBTITLE</b> EuO-Based Multifunctional Heterostructures				<b>5a. CONTRACT NUMBER</b> FA9550-10-1-0123	
				<b>5b. GRANT NUMBER</b> FA9550-10-1-0123	
				<b>5c. PROGRAM ELEMENT NUMBER</b>	
				<b>5d. PROJECT NUMBER</b>	
<b>6. AUTHOR(S)</b> Schlom, Darrell G.				<b>5e. TASK NUMBER</b>	
				<b>5f. WORK UNIT NUMBER</b>	
<b>7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)</b> Office of Sponsored Programs 373 Pine Tree Rd Cornell University Ithaca, NY 14850-2820				<b>8. PERFORMING ORGANIZATION REPORT NUMBER</b>  OSP 59872	
<b>9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)</b> USAF, AFRL DUNS 143574726 AF Office of Scientific Research 875 N. Randolph St. Room 3112 Arlington, VA 22230 Emily R. Bannan 703-696-5957, emily.bannan@us.af.mil				<b>10. SPONSOR/MONITOR'S ACRONYM(S)</b>	
				<b>11. SPONSOR/MONITOR'S REPORT NUMBER(S)</b>	
<b>12. DISTRIBUTION/AVAILABILITY STATEMENT</b> Approved for public release. Copyright is held by the author and a license is granted to the government.					
<b>13. SUPPLEMENTARY NOTES</b> None					
<b>14. ABSTRACT</b> Using molecular-beam epitaxy heterostructures were grown in which EuO was controllably doped, strained, patterned, and integrated with other materials to enable novel effects and emerging device concepts to be explored. These included (1) achieving a drastic increase of the magnetoresistance and the metal-insulator transition resistance ratios of doped EuO by interfacing this semiconductor with niobium; the observed effect is general and may be applied to any metal/semiconductor interface where the semiconductor shows large Zeeman splitting under magnetic field, (2) understanding the changes in electronic structure and Fermi-surface reconstruction that occur as doped EuO progresses through the ferromagnetic metal-insulator transition; a lack of carrier activation arises from defect states near the $\Gamma$ point, (3) demonstrating that ultrafast optical pulses can be used to strengthen or weaken the magnetic order of doped EuO by $\sim 10\%$ in $< 3$ ps, (4) establishing a new method for making EuO films by high-vacuum techniques with perfection and properties previously accessible only by ultra-high vacuum methods, and (5) straining EuO by over 6% to achieve the simplest and highest temperature strong multiferroic known (simultaneously ferromagnetic and ferroelectric).					
<b>15. SUBJECT TERMS</b>					
<b>16. SECURITY CLASSIFICATION OF:</b>			<b>17. LIMITATION OF ABSTRACT</b>  UU	<b>18. NUMBER OF PAGES</b>  6	<b>19a. NAME OF RESPONSIBLE PERSON</b> Darrell G. Schlom
<b>a. REPORT</b>  U	<b>b. ABSTRACT</b>  U	<b>c. THIS PAGE</b>  U			<b>19b. TELEPHONE NUMBER (Include area code)</b> 607-255-6504

Reset

## INSTRUCTIONS FOR COMPLETING SF 298

**1. REPORT DATE.** Full publication date, including day, month, if available. Must cite at least the year and be Year 2000 compliant, e.g. 30-06-1998; xx-06-1998; xx-xx-1998.

**2. REPORT TYPE.** State the type of report, such as final, technical, interim, memorandum, master's thesis, progress, quarterly, research, special, group study, etc.

**3. DATES COVERED.** Indicate the time during which the work was performed and the report was written, e.g., Jun 1997 - Jun 1998; 1-10 Jun 1996; May - Nov 1998; Nov 1998.

**4. TITLE.** Enter title and subtitle with volume number and part number, if applicable. On classified documents, enter the title classification in parentheses.

**5a. CONTRACT NUMBER.** Enter all contract numbers as they appear in the report, e.g. F33615-86-C-5169.

**5b. GRANT NUMBER.** Enter all grant numbers as they appear in the report, e.g. AFOSR-82-1234.

**5c. PROGRAM ELEMENT NUMBER.** Enter all program element numbers as they appear in the report, e.g. 61101A.

**5d. PROJECT NUMBER.** Enter all project numbers as they appear in the report, e.g. 1F665702D1257; ILIR.

**5e. TASK NUMBER.** Enter all task numbers as they appear in the report, e.g. 05; RF0330201; T4112.

**5f. WORK UNIT NUMBER.** Enter all work unit numbers as they appear in the report, e.g. 001; AFAPL30480105.

**6. AUTHOR(S).** Enter name(s) of person(s) responsible for writing the report, performing the research, or credited with the content of the report. The form of entry is the last name, first name, middle initial, and additional qualifiers separated by commas, e.g. Smith, Richard, J, Jr.

**7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES).** Self-explanatory.

**8. PERFORMING ORGANIZATION REPORT NUMBER.** Enter all unique alphanumeric report numbers assigned by the performing organization, e.g. BRL-1234; AFWL-TR-85-4017-Vol-21-PT-2.

**9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES).** Enter the name and address of the organization(s) financially responsible for and monitoring the work.

**10. SPONSOR/MONITOR'S ACRONYM(S).** Enter, if available, e.g. BRL, ARDEC, NADC.

**11. SPONSOR/MONITOR'S REPORT NUMBER(S).** Enter report number as assigned by the sponsoring/monitoring agency, if available, e.g. BRL-TR-829; -215.

**12. DISTRIBUTION/AVAILABILITY STATEMENT.** Use agency-mandated availability statements to indicate the public availability or distribution limitations of the report. If additional limitations/ restrictions or special markings are indicated, follow agency authorization procedures, e.g. RD/FRD, PROPIN, ITAR, etc. Include copyright information.

**13. SUPPLEMENTARY NOTES.** Enter information not included elsewhere such as: prepared in cooperation with; translation of; report supersedes; old edition number, etc.

**14. ABSTRACT.** A brief (approximately 200 words) factual summary of the most significant information.

**15. SUBJECT TERMS.** Key words or phrases identifying major concepts in the report.

**16. SECURITY CLASSIFICATION.** Enter security classification in accordance with security classification regulations, e.g. U, C, S, etc. If this form contains classified information, stamp classification level on the top and bottom of this page.

**17. LIMITATION OF ABSTRACT.** This block must be completed to assign a distribution limitation to the abstract. Enter UU (Unclassified Unlimited) or SAR (Same as Report). An entry in this block is necessary if the abstract is to be limited.

## Final Report

### ABSTRACT

Using molecular-beam epitaxy heterostructures were grown in which EuO was controllably doped, strained, patterned, and integrated with other materials to enable novel effects and emerging device concepts to be explored. These included (1) achieving a drastic increase of the magnetoresistance and the metal-insulator transition resistance ratios of doped EuO by interfacing this semiconductor with niobium; the observed effect is general and may be applied to any metal/semiconductor interface where the semiconductor shows large Zeeman splitting under magnetic field, (2) understanding the changes in electronic structure and Fermi-surface reconstruction that occur as doped EuO progresses through the ferromagnetic metal-insulator transition; a lack of carrier activation arises from defect states near the  $\Gamma$  point, (3) demonstrating that ultrafast optical pulses can be used to strengthen or weaken the magnetic order of doped EuO by  $\sim 10\%$  in  $<3$  ps, (4) establishing a new method for making EuO films by high-vacuum techniques with perfection and properties previously accessible only by ultra-high vacuum methods, and (5) straining EuO by over 6% to achieve the simplest and highest temperature strong multiferroic known (simultaneously ferromagnetic and ferroelectric).

### INTRODUCTION

EuO has long been realized to have exceptional optical, magnetic, and electronic properties as well as coupled charge-spin-lattice properties that are relevant to optical switching, spintronics, and emerging devices.<sup>1</sup> For example, EuO has (1) a metal-insulator transition with the largest change in resistance ( $\Delta R/R > 10^{13}$ ) of any material,<sup>2,3</sup> (2) the largest Verdet constant ( $v=4\times 10^5$  ° (T·cm)<sup>-1</sup>)—a measure of the strength of the Faraday effect,<sup>4</sup> and (3) the second highest spin polarization ( $>90\%$ , which we updated to  $>96\%$  with the support of this AFOSR program<sup>5</sup>) of any known material.<sup>6</sup> Although its ferromagnetic transition temperature is relatively low (69 K),<sup>7</sup> because it exhibits the highest known coefficients for many properties, its development in semiconductor-quality form will enable it to be used as a model system to allow novel effects and emerging device concepts to be explored. In this program we have perfected the growth of EuO using molecular-beam epitaxy (MBE) and developed semiconductor-grade heterostructures in which EuO can be controllably doped, strained, patterned, and epitaxially integrated with other metals, semiconductors, and insulators to enable bandgap engineering concepts to be applied to this unusual II-VI semiconductor. As we have developed a materials technology base for EuO, we have supplied appropriate samples to numerous collaborators around the world to enable novel effects and emerging device concepts to be explored.

### KEY PERSONNEL

The numerous collaborations enabled by this AFOSR program have led to 15 published papers in refereed journals<sup>5,8-21</sup> including two in *Nature Communications*,<sup>20,21</sup> two in *Physical Review Letters*,<sup>9,13</sup> and one in *Advanced Materials*.<sup>10</sup> At Cornell the support of this AFOSR program led to the Ph.D. thesis of Alex Melville, who is now employed at MIT Lincoln Laboratory. Alex's Ph.D. thesis was entitled *Assessing the Effects of Biaxial Strain and Chemical Doping on the Magnetic and Electronic Properties of Epitaxial Europium Monoxide Films*. It also partially supported postdoc Dr. Rainer Held. Key among our collaborators was Dr. Andreas Schmehl in Jochen Mannhart's group at the University of Augsburg, who completed his Habilitation Degree entitled *Studies on Europium Monoxide—A Key Material for the Understanding of Magneto-Electronic Materials, Heterostructures and Interfaces*. Andreas had a graduate student working with him, Thomás Mairoser, who during this program completed his

Ph.D. dedicated to the electrical transport measurements (Hall and magnetization) of doped EuO films to help us establish the optimal growth conditions for the controlled growth of rare-earth-doped EuO films. Thomás' Ph.D. thesis is entitled *In Situ Neutronen-Reflektometrie und Untersuchungen von EuO-Filmen*.

### RESEARCH HIGHLIGHTS

Together with the collaborators in Jochen Mannhart's group at the University of Augsburg, Germany and collaborators at Cornell we attempted to answer the key question for higher-temperature applications of EuO, "Is there an intrinsic limit to the charge carrier-induced increase of the Curie temperature of EuO?"<sup>9</sup> Rare earth doping is the key strategy to increase the Curie temperature ( $T_c$ ) of the ferromagnetic semiconductor EuO. The interplay between doping and charge carrier density ( $n$ ), and the limit of the  $T_c$  increase, however, are yet to be understood. Using a combination of Hall effect, x-ray absorption spectroscopy, and SQUID we measured  $n$  and  $T_c$  of Gd-doped EuO over a wide range of doping levels. The results show a direct correlation between  $n$  and  $T_c$ , with both exhibiting a maximum at high doping. On average, less than 35% of the dopants act as donors (with the rest being electrically inactive!), raising the question about the limit to increasing  $T_c$ .

Also in collaboration with Jochen Mannhart's group at the University of Augsburg, Germany we have worked to increase magnetoresistance using magnetic-field-tunable interface.<sup>10</sup> Although the  $T_c$  of EuO can be increased significantly with rare-earth doping, this increase comes at the cost of drastically reduced resistance ratios, both for the colossal magnetoresistive effect and the metal-to-insulator transition (MIT). We found a way, however, to overcome this intrinsic predicament. We achieved a drastic increase of the magnetoresistance and the MIT resistance ratios of bulk  $\text{Eu}_{0.99}\text{La}_{0.01}\text{O}$  by interfacing this semiconductor with niobium. The transparency of this interface critically depends on the large Zeeman splitting of the  $\text{Eu}_{0.99}\text{La}_{0.01}\text{O}$  conduction band, allowing for the temperature and magnetic field induced switching between non-linear and linear current-voltage characteristics, associated with tunneling-dominated and metallic transport across the interface.

In collaboration with Manfred Fiebig's group at the University of Bonn, Germany we have seen a large nonlinear magneto-optical effect in the centrosymmetric ferromagnetic semiconductor EuO.<sup>8,12,14</sup> Although EuO is known for its huge Verdet coefficient and associated magneto-optic effects, surprisingly it had *never* before been characterized by nonlinear optical techniques. Doing so on our high quality EuO films, our collaborators observed pronounced magnetic-dipole-induced second-harmonic generation (SHG). The SHG light wave emerges background-free at the Curie temperature and couples linearly to the spontaneous magnetization. The SHG spectrum is determined by spin-allowed and spin-forbidden transitions between the  $4f$  ground state and the  $5d(t_{2g})$  states of the  $\text{Eu}^{2+}$  ion. At the coercive field, components of the spontaneous magnetization perpendicular to the applied field are observed. Spatially resolved hysteresis measurements reveal that the ferromagnetic domains possess an average extension of  $<1\ \mu\text{m}$  although pinning effects can stabilize domains that are two orders of magnitude larger.<sup>14</sup>

Also in collaboration with Manfred Fiebig's group (which during this project moved to the Swiss Federal Institute of Technology in Zurich, Switzerland) we have tuned ferromagnetism optically.<sup>20</sup> Interest in manipulating the magnetic order by ultrashort laser pulses has thrived since it was observed that such pulses can be used to alter the magnetization on a sub-picosecond timescale. Usually this involves demagnetization by laser heating or, in rare cases, a transient increase of magnetization. What we demonstrated is a mechanism that allows the magnetic order of a material to be enhanced or attenuated at will. This is possible in systems simultaneously

possessing a low, tunable density of conduction band carriers and a high density of magnetic moments. In such systems, the thermalization time can be set such that adiabatic processes dominate the photoinduced change of the magnetic order—the three-temperature model for interacting thermalized electron, spin and lattice reservoirs is bypassed. In ferromagnetic  $\text{Eu}_{1-x}\text{Gd}_x\text{O}$ , we demonstrated the strengthening as well as the weakening of the magnetic order by  $\sim 10\%$  and within  $<3$  ps by optically controlling the magnetic exchange interaction.<sup>20</sup>

In collaboration with Jochen Mannhart's group we found a way to extend the large metal-to-insulator transition (MIT) of EuO to higher temperatures.<sup>8</sup> Using rare-earth doping, the Curie temperature ( $T_C$ ) of EuO can be increased from 69 K to  $\sim 170$  K.<sup>22,23</sup> This increase, however, comes at the cost of drastically reduced resistance ratios, both for the CMR effect and the MIT.<sup>6</sup> We found a way to overcome this intrinsic predicament. We were able to achieve a drastic increase of the magnetoresistance and the MIT resistance ratios of bulk  $\text{Eu}_{0.99}\text{La}_{0.01}\text{O}$  by interfacing this semiconductor with niobium.<sup>8</sup> The transparency of this interface critically depends on the large Zeeman splitting of the  $\text{Eu}_{0.99}\text{La}_{0.01}\text{O}$  conduction band,<sup>24,25</sup> allowing for the temperature and magnetic field induced switching between non-linear and linear current-voltage characteristics, associated with tunneling-dominated and metallic transport across the interface.<sup>8</sup> The result is an enhanced magnetoresistance and metal-to-insulator transition in highly electron-doped europium monoxide by interfacing it with niobium. By optimizing the rare-earth doping level, the interface properties are tuned to the point, at which changes of the band structure and of the charge carrier density cause a transition of the interface between tunneling-dominated and metallic transport. The doping levels necessary for achieving these improved properties are high enough to benefit from the carrier-mediated increase in Curie temperature. This same principle is applicable to any metal/semiconductor interface where the semiconductor shows large Zeeman splitting under magnetic field, e.g., dilute magnetic semiconductors.

Also in collaboration with Jochen Mannhart's group we studied the influence of the substrate temperature on the Curie temperature and charge carrier density of epitaxial Gd-doped EuO films.<sup>11</sup> Rare earth doping is a standard, yet experimentally poorly understood method to increase the Curie temperature ( $T_C$ ) of the ferromagnetic semiconductor EuO. We investigated the dependence of the charge carrier density ( $n$ ) and the  $T_C$  of 4.2 at. % Gd-doped EuO films grown by MBE on (110)-oriented  $\text{YAlO}_3$  on substrate temperature ( $T_{\text{sub}}$ ). Increasing  $T_{\text{sub}}$  leads to a decrease in  $n$  and  $T_C$ . For high substrate temperatures the Gd-doping is rendered completely inactive:  $n$  and  $T_C$  drop to the values of undoped EuO.

In collaboration with Kyle Shen's group at Cornell University, who has connected an angle-resolved photoemission spectroscopy (ARPES) system to our oxide MBE, we have determined the temperature dependence of the electronic structure and Fermi-surface reconstruction of  $\text{Eu}_{1-x}\text{Gd}_x\text{O}$  through the ferromagnetic metal-insulator transition.<sup>13</sup> This capability enabled us to measure the ARPES spectra of  $\text{Eu}_{1-x}\text{Gd}_x\text{O}$  through the ferromagnetic metal-insulator transition. In the ferromagnetic phase, we observed Fermi surface pockets at the Brillouin zone boundary, consistent with density functional theory, which predicts a half metal. Upon warming into the paramagnetic state, our results reveal a strong momentum-dependent evolution of the electronic structure, where the metallic states at the zone boundary are replaced by pseudogapped states at the Brillouin zone center due to the absence of magnetic long-range order of the Eu 4f moments.<sup>13</sup>

In collaboration with Jochen Mannhart's group at the University of Augsburg we studied the effect of lutetium doping on the structural, electronic, and magnetic properties of epitaxial EuO thin films grown by reactive molecular-beam epitaxy.<sup>5</sup> The behavior of Lu-doped EuO was

contrasted with doping by lanthanum and gadolinium. All three dopants were found to behave similarly despite differences in electronic configuration and ionic size. Andreev reflection measurements on Lu-doped EuO revealed a spin-polarization of 96% in the conduction band, despite non-magnetic carriers introduced by 5% lutetium doping.<sup>5</sup> This high spin polarization, second only to CrO<sub>2</sub> with 98% spin polarization,<sup>26</sup> is in agreement with previous reports of the near-complete spin-polarization of EuO.<sup>6</sup> The high spin-polarization despite 5% doping of nonmagnetic atoms is critically important, as it shows that EuO retains its high spin-polarization in the presence of a dopant which significantly boosts its  $T_C$ . This is not so surprising given that doped EuO is a half-metal due to the spin-splitting of the conduction band,<sup>25,27</sup> so the carriers are spin-polarized anyway despite the nature of the dopant.

We further showed how the transition temperature of EuO could be shifted by biaxial strain in epitaxial films,<sup>16</sup> epitaxially integrated EuO with diamond,<sup>18</sup> and in collaboration with David Muller's group at Cornell succeeded in imaging EuO for the first time by transmission electron microscopy.<sup>19</sup> Spin injection is greatly affected by the quality of the interface between the injector and silicon. Using atomic-resolution scanning transmission electron microscopy in conjunction with electron energy loss spectroscopy we directly imaged and chemically characterized a series of EuO/Si and EuO/YAlO<sub>3</sub> interfaces fabricated using different growth conditions.<sup>19</sup> We identified the presence of europium silicides and regions of disorder at the EuO/Si interfaces, imperfections that could significantly reduce spin injection efficiencies via spin-flip scattering.

Finally, in collaboration with Andreas Schmehl and Thomás Mairoser at the University of Augsburg in Germany, we discovered a way to make high quality epitaxial EuO films via a topotactic transformation of epitaxial Eu<sub>2</sub>O<sub>3</sub> films.<sup>21</sup> Epitaxy is widely employed to create highly oriented crystalline films. A less appreciated, but nonetheless powerful means of creating such films is via topotactic transformation, in which a chemical reaction transforms a single crystal of one phase into a single crystal of a different phase, which inherits its orientation from the original crystal. Topotactic reactions may be applied to epitaxial films to substitute, add, or remove ions to yield epitaxial films of different phases. We exploited a topotactic reduction reaction to provide a non-ultra-high vacuum (non-UHV) means of growing highly oriented single crystalline thin films of the easily over-oxidized half-metallic semiconductor EuO with a perfection rivalling that of the best films of the same material grown by molecular-beam epitaxy or UHV pulsed-laser deposition. As the technique only requires high-vacuum deposition equipment, it has the potential to drastically improve the accessibility of high-quality single crystalline films of EuO as well as other difficult to synthesize compounds.<sup>21</sup>

## REFERENCES

- <sup>1</sup> P.A. Grünberg, "Nobel Lecture: From Spin Waves to Giant Magnetoresistance and Beyond," *Rev. Mod. Phys.* **80** (2008) 1531-1540.
- <sup>2</sup> G. Petrich, S. von Molnár, and T. Penney, "Exchange-Induced Autoionization in Eu-Rich EuO," *Phys. Rev. Lett.* **26** (1971) 885-888.
- <sup>3</sup> M.W. Shafer, J.B. Torrance, and T. Penney, "Relationship of Crystal Growth Parameters to the Stoichiometry of EuO as Determined by I.R. and Conductivity Measurements," *J. Phys. Chem. Solids* **33** (1972) 2251-2266.
- <sup>4</sup> K.Y. Ahn, and M.W. Shafer, "Relationship between Stoichiometry and Properties of EuO Films," *J. Appl. Phys.* **41** (1970) 1260-1262.



- <sup>5</sup> A. Melville, T. Mairoser, A. Schmehl, D.E. Shai, E.J. Monkman, J.W. Harter, T. Heeg, B. Holländer, J. Schubert, K.M. Shen, J. Mannhart, and D.G. Schlom, "Lutetium-doped EuO Films Grown by Molecular-Beam Epitaxy," *Appl. Phys. Lett.* (2012) 222101.
- <sup>6</sup> A. Schmehl, V. Vaithyanathan, A. Herrnberger, S. Thiel, C. Richter, M. Liberati, T. Heeg, M. Röckerath, L. Fitting Kourkoutis, S. Mühlbauer, P. Böni, D.A. Muller, Y. Barash, J. Schubert, Y. Idzerda, J. Mannhart, and D.G. Schlom, "Epitaxial Integration of the Highly Spin-Polarized Ferromagnetic Semiconductor EuO with Silicon and GaN," *Nature Mater.* **6** (2007) 882-887.
- <sup>7</sup> B.T. Matthias, R.M. Bozorth, and J.H. Van Vleck, "Ferromagnetic Interaction in EuO," *Phys. Rev. Lett.* **7** (1961) 160-161.
- <sup>8</sup> M. Matsubara, A. Schmehl, J. Mannhart, D.G. Schlom, and M. Fiebig, "Large Nonlinear Magneto-Optical Effect in the Centrosymmetric Ferromagnetic Semiconductor EuO," *Phys. Rev. B* **81** (2010) 214447.
- <sup>9</sup> T. Mairoser, A. Schmehl, A. Melville, T. Heeg, L. Canella, P. Böni, W. Zander, J. Schubert, D.E. Shai, E.J. Monkman, K.M. Shen, D.G. Schlom, and J. Mannhart, "Is there an Intrinsic Limit to the Charge-Carrier-Induced Increase of the Curie Temperature of EuO?," *Phys. Rev. Lett.* **105** (2010) 257206.
- <sup>10</sup> A. Schmehl, D.G. Schlom, and J. Mannhart, "Increasing Magnetoresistance Using Magnetic-Field-Tunable Interfaces," *Adv. Mater.* **23** (2011) 1242-1245.
- <sup>11</sup> T. Mairoser, A. Schmehl, A. Melville, T. Heeg, W. Zander, J. Schubert, D.E. Shai, E.J. Monkman, K.M. Shen, T.Z. Regier, D.G. Schlom, and J. Mannhart, "Influence of the Substrate Temperature on the Curie Temperature and Charge Carrier Density of Epitaxial Gd-Doped EuO Films," *Appl. Phys. Lett.* **98** (2011) 102110.
- <sup>12</sup> M. Matsubara, C. Becher, A. Schmehl, J. Mannhart, D.G. Schlom, and M. Fiebig, "Optical Second- and Third-Harmonic Generation on the Ferromagnetic Semiconductor Europium Oxide," *J. Appl. Phys.* **109** (2011) 07C309.
- <sup>13</sup> D.E. Shai, A.J. Melville, J.W. Harter, E.J. Monkman, D.W. Shen, A. Schmehl, D.G. Schlom, and K.M. Shen, "Temperature Dependence of the Electronic Structure and Fermi-Surface Reconstruction of  $\text{Eu}_{1-x}\text{Gd}_x\text{O}$  through the Ferromagnetic Metal-Insulator Transition," *Phys. Rev. Lett.* **108** (2012) 267003.
- <sup>14</sup> M. Matsubara, A. Schmehl, J. Mannhart, D.G. Schlom, and M. Fiebig, "Giant Third-Order Magneto-Optical Rotation in Ferromagnetic EuO," *Phys. Rev. B* **86** (2012) 195127.
- <sup>15</sup> T. Mairoser, F. Loder, A. Melville, D.G. Schlom, and A. Schmehl, "Influence of Chemical Doping on the Magnetic Properties of EuO," *Phys. Rev. B* **87** (2013) 014416.
- <sup>16</sup> A. Melville, T. Mairoser, A. Schmehl, T. Birol, T. Heeg, B. Holländer, J. Schubert, C.J. Fennie, and D.G. Schlom, "Effect of Film Thickness and Biaxial Strain on the Curie Temperature of EuO," *Appl. Phys. Lett.* **102** (2013) 062404.
- <sup>17</sup> D.M. Kaz, C.G. Bischak, C.L. Hetherington, H.H. Howard, X. Marti, J.D. Clarkson, C. Adamo, D.G. Schlom, R. Ramesh, S. Aloni, D.F. Ogletree, and N.S. Ginsberg, "Bright Cathodoluminescent Thin Films for Scanning Nano-Optical Excitation and Imaging," *ACS Nano* **7** (2013) 10397-10404.
- <sup>18</sup> A. Melville, T. Mairoser, A. Schmehl, M. Fischer, S. Gsell, M. Schreck, D.D. Awschalom, T. Heeg, B. Holländer, J. Schubert, and D.G. Schlom, "Epitaxial Growth of Europium Monoxide on Diamond," *Appl. Phys. Lett.* **103** (2013) 222402.
- <sup>19</sup> J.A. Mundy, D. Hodash, A. Melville, R. Held, T. Mairoser, D.A. Muller, L.F. Kourkoutis, A. Schmehl, and D.G. Schlom, "Hetero-Epitaxial EuO Interfaces Studied by Analytic Electron Microscopy," *Appl. Phys. Lett.* **104** (2014) 091601.



- <sup>20</sup> M. Matsubara, A. Schroer, A. Schmehl, A. Melville, C. Becher, M.T. Martinez, D.G. Schlom, J. Mannhart, J. Kroha, and M. Fiebig, “Ultrafast Optical Tuning of Ferromagnetism via the Carrier Density,” *Nature Commun.* **6** (2015) 6724.
- <sup>21</sup> T. Mairoser, J.A. Mundy, A. Melville, D. Hodash, P. Cueva, R. Held, A. Glavic, J. Schubert, D.A. Muller, D.G. Schlom, and A. Schmehl, “High-Quality EuO Thin Films the Easy Way via Topotactic Transformation,” *Nature Commun.* (in press, 2015).
- <sup>22</sup> T.R. McGuire, and M.W. Shafer, “Ferromagnetic Europium Compounds,” *J. Appl. Phys.* **35** (1964) 984–988.
- <sup>23</sup> H. Ott, S.J. Heise, R. Sutarto, Z. Hu, C.F. Chang, H.H. Hsieh, H.-J. Lin, C.T. Chen, and L.H. Tjeng, “Soft X-Ray Magnetic Circular Dichroism Study on Gd-Doped EuO Thin Films,” *Phys. Rev. B* **73** (2006) 094407.
- <sup>24</sup> J. Schoenes and P. Wachter, “Exchange Optics in Gd-Doped EuO,” *Phys. Rev. B* **9** (1974) 3097-3105.
- <sup>25</sup> P.G. Steeneken, L.H. Tjeng, I. Elfimov, G.A. Sawatzky, G. Ghiringhelli, N.B. Brookes, and D.-J. Huang, “Exchange Splitting and Charge Carrier Spin Polarization in EuO,” *Phys. Rev. Lett.* **88** (2002) 047201.
- <sup>26</sup> A. Anguelouch, A. Gupta, G. Xiao, G. X. Miao, D. W. Abraham, S. Ingvarsson, Y. Ji, and C. L. Chien, “Properties of Epitaxial Chromium Dioxide Films Grown by Chemical Vapor Deposition using a Liquid Precursor,” *J. Appl. Phys.* **91** (2002) 7140-7142.
- <sup>27</sup> S. von Molnár, “Transport Properties of the Europium Chalcogenides,” *IBM J. Res. Develop.* **14** (1970) 269–275.

1.

**1. Report Type**

Final Report

**Primary Contact E-mail****Contact email if there is a problem with the report.**

schlom@cornell.edu

**Primary Contact Phone Number****Contact phone number if there is a problem with the report**

607-255-6504

**Organization / Institution name**

Cornell University

**Grant/Contract Title****The full title of the funded effort.**

EuO-Based Multifunctional Heterostructures

**Grant/Contract Number****AFOSR assigned control number. It must begin with "FA9550" or "F49620" or "FA2386".**

FA9550-10-1-0123

**Principal Investigator Name****The full name of the principal investigator on the grant or contract.**

Darrell G. Schlom

**Program Manager****The AFOSR Program Manager currently assigned to the award**

Kenneth C. Goretta

**Reporting Period Start Date**

4/15/2010

**Reporting Period End Date**

04/14/2015

**Abstract**

Using molecular-beam epitaxy heterostructures were grown in which EuO was controllably doped, strained, patterned, and integrated with other materials to enable novel effects and emerging device concepts to be explored. These included (1) achieving a drastic increase of the magnetoresistance and the metal-insulator transition resistance ratios of doped EuO by interfacing this semiconductor with niobium; the observed effect is general and may be applied to any metal/semiconductor interface where the semiconductor shows large Zeeman splitting under magnetic field, (2) understanding the changes in electronic structure and Fermi-surface reconstruction that occur as doped EuO progresses through the ferromagnetic metal-insulator transition; a lack of carrier activation arises from defect states near the  $\Gamma$  point, (3) demonstrating that ultrafast optical pulses can be used to strengthen or weaken the magnetic order of doped EuO by  $\sim 10\%$  in  $< 3$  ps, (4) establishing a new method for making EuO films by high-vacuum techniques with perfection and properties previously accessible only by ultra-high vacuum methods, and (5) straining EuO by over 6% to achieve the simplest and highest temperature strong multiferroic known (simultaneously ferromagnetic and ferroelectric).

**Distribution Statement****This is block 12 on the SF298 form.**

### Explanation for Distribution Statement

If this is not approved for public release, please provide a short explanation. E.g., contains proprietary information.

### SF298 Form

Please attach your [SF298](#) form. A blank SF298 can be found [here](#). Please do not password protect or secure the PDF. The maximum file size for an SF298 is 50MB.

[AFD-070820-035 Form.pdf](#)

**Upload the Report Document. File must be a PDF. Please do not password protect or secure the PDF. The maximum file size for the Report Document is 50MB.**

[Final Report.pdf](#)

**Upload a Report Document, if any. The maximum file size for the Report Document is 50MB.**

### Archival Publications (published) during reporting period:

1. M. Matsubara, A. Schmehl, J. Mannhart, D.G. Schlom, and M. Fiebig, "Large Nonlinear Magneto-Optical Effect in the Centrosymmetric Ferromagnetic Semiconductor EuO," *Physical Review B* 81 (2010) 214447.
2. T. Mairoser, A. Schmehl, A. Melville, T. Heeg, L. Canella, P. Böni, W. Zander, J. Schubert, D.E. Shai, E.J. Monkman, K.M. Shen, D.G. Schlom, and J. Mannhart, "Is there an Intrinsic Limit to the Charge-Carrier-Induced Increase of the Curie Temperature of EuO?," *Physical Review Letters* 105 (2010) 257206.
3. A. Schmehl, D.G. Schlom, and J. Mannhart, "Increasing Magnetoresistance Using Magnetic-Field-Tunable Interfaces," *Advanced Materials* 23 (2011) 1242-1245.
4. T. Mairoser, A. Schmehl, A. Melville, T. Heeg, W. Zander, J. Schubert, D.E. Shai, E.J. Monkman, K.M. Shen, T.Z. Regier, D.G. Schlom, and J. Mannhart, "Influence of the Substrate Temperature on the Curie Temperature and Charge Carrier Density of Epitaxial Gd-Doped EuO Films," *Applied Physics Letters* 98 (2011) 102110.
5. M. Matsubara, C. Becher, A. Schmehl, J. Mannhart, D.G. Schlom, and M. Fiebig, "Optical Second- and Third-Harmonic Generation on the Ferromagnetic Semiconductor Europium Oxide," *Journal of Applied Physics* 109 (2011) 07C309.
6. A. Melville, T. Mairoser, A. Schmehl, D.E. Shai, E.J. Monkman, J.W. Harter, T. Heeg, B. Holländer, J. Schubert, K.M. Shen, J. Mannhart, and D.G. Schlom, "Lutetium-doped EuO Films Grown by Molecular-Beam Epitaxy," *Applied Physics Letters* (2012) 222101.
7. D.E. Shai, A.J. Melville, J.W. Harter, E.J. Monkman, D.W. Shen, A. Schmehl, D.G. Schlom, and K.M. Shen, "Temperature Dependence of the Electronic Structure and Fermi-Surface Reconstruction of  $\text{Eu}_{1-x}\text{Gd}_x\text{O}$  through the Ferromagnetic Metal-Insulator Transition," *Physical Review Letters* 108 (2012) 267003.
8. M. Matsubara, A. Schmehl, J. Mannhart, D.G. Schlom, and M. Fiebig, "Giant Third-Order Magneto-Optical Rotation in Ferromagnetic EuO," *Physical Review B* 86 (2012) 195127.
9. T. Mairoser, F. Loder, A. Melville, D.G. Schlom, and A. Schmehl, "Influence of Chemical Doping on the Magnetic Properties of EuO," *Physical Review B* 87 (2013) 014416.
10. A. Melville, T. Mairoser, A. Schmehl, T. Birol, T. Heeg, B. Holländer, J. Schubert, C.J. Fennie, and D.G. Schlom, "Effect of Film Thickness and Biaxial Strain on the Curie Temperature of EuO," *Applied Physics Letters* 102 (2013) 062404.
11. D.M. Kaz, C.G. Bischak, C.L. Hetherington, H.H. Howard, X. Marti, J.D. Clarkson, C. Adamo, D.G.

Schlom, R. Ramesh, S. Aloni, D.F. Ogletree, and N.S. Ginsberg, "Bright Cathodoluminescent Thin Films for Scanning Nano-Optical Excitation and Imaging," ACS Nano 7 (2013) 10397-10404.

12. A. Melville, T. Mairoser, A. Schmehl, M. Fischer, S. Gsell, M. Schreck, D.D. Awschalom, T. Heeg, B. Holländer, J. Schubert, and D.G. Schlom, "Epitaxial Growth of Europium Monoxide on Diamond," Applied Physics Letters 103 (2013) 222402.

13. J.A. Mundy, D. Hodash, A. Melville, R. Held, T. Mairoser, D.A. Muller, L.F. Kourkoutis, A. Schmehl, and D.G. Schlom, "Hetero-Epitaxial EuO Interfaces Studied by Analytic Electron Microscopy," Applied Physics Letters 104 (2014) 091601.

14. M. Matsubara, A. Schroer, A. Schmehl, A. Melville, C. Becher, M.T. Martinez, D.G. Schlom, J. Mannhart, J. Kroha, and M. Fiebig, "Ultrafast Optical Tuning of Ferromagnetism via the Carrier Density," Nature Communications 6 (2015) 6724.

15. T. Mairoser, J.A. Mundy, A. Melville, D. Hodash, P. Cueva, R. Held, A. Glavic, J. Schubert, D.A. Muller, D.G. Schlom, and A. Schmehl, "High-Quality EuO Thin Films the Easy Way via Topotactic Transformation," Nature Communications (in press, 2015).

**Changes in research objectives (if any):**

none

**Change in AFOSR Program Manager, if any:**

Kitt Reinhardt --> James Hwang --> Kenneth C. Goretta

**Extensions granted or milestones slipped, if any:**

none

**AFOSR LRIR Number**

**LRIR Title**

**Reporting Period**

**Laboratory Task Manager**

**Program Officer**

**Research Objectives**

**Technical Summary**

**Funding Summary by Cost Category (by FY, \$K)**

	Starting FY	FY+1	FY+2
Salary			
Equipment/Facilities			
Supplies			
Total			

**Report Document**

**Report Document - Text Analysis**

**Report Document - Text Analysis**

**Appendix Documents**

**2. Thank You**

**E-mail user**

Jun 16, 2015 18:54:15 Success: Email Sent to: schlom@cornell.edu